

July 26, 2011

P.O. Box 131359 • Tyler, CR 2120, Texas 75713, Phone 903.534.8021 • Fax 903.581.4376

Product Data Sheet



NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor does it serve as a license to operate any patent. Due to widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suitability. Product typical properties in this publication are current.

SYNTHETIC AIR COMPRESSOR

SUPRA-26N

Summit Supra-26N has been formulated to address the specific problems associated with centrifugal compressor lubricants - thermal degradation and deposit formation. The polyglycol/ester blend has provided superior performance in the areas of oxidation resistance and deposit formation.

Physical Properties

PRODUCT	SUPRA-26N
Viscosity	
@ 40°C, cSt	26.5
@ 100°C, cSt	5.4
@ 100°F, SUS	136
@ 210°F, SUS	44.2
Viscosity Index	141
Specific Gravity	0.9593
Density, lbs/gal	7.989
Pour Point, °F (°C)	-69 (-56)
Flash Point, °F (°C)	485 (252)